

# SUBMITTAL

## EPDM Style AB-563

**Manufacturer – American Biltrite**

Gaskets meet the pressure ratings, drilling and dimensions of ANSI/ASME B16.2.1

### Style AB-563

EPDM (Black)

#### Media

- Animal and Vegetable oils
- Water
- Steam
- Oxygenated solvents



#### Specifications

Max. Temperature:	225	(° F)
Hardness Shore A	60	
Tensile Strength ASTM D-412	1000	(PSI)
Elongation	500	%

#### Availability

Full Face     Ring     1/16" Thick     1/8" Thick     1/4" Thick

#### Benefits

Commercial Grade

- Excellent for applications in which involve extreme temperature and or weather conditions. It's used extensively in high temperature installations.
- Offers ozone and chemical resistance as well as resistance to high temperatures.
- Also provides excellent electrical and dynamic properties.

**TRIPAC**

475 Klug Circle-Corona, CA. 92880 (951) 280-4488 - Fax: (951) 272-4445